

PRODUCT CODES: ELSEAL550

NAME: ENVIROCRYL 550 CLEAR NO-SAG CHAIR SEALER

DESCRIPTION: ELSEAL550 No-Sag Sealer is a fast drying one-component acrylic sealer for use in vertical spray applications. Used as supplied, this sealer can be applied at much higher coat weights than conventional finishes (8 wet mils). The product provides good clarity and sanding as well as fast dry times that are suitable for high volume production environments.

USES: This product is designed for interior wood finishing applications and is especially suited for furniture sprayed on a hanging line or conveyor where furniture is sprayed assembled and complex shapes cause lower viscosity products to sag or run.

PRODUCT PREPARATION: Reduction is not required. Product should be at room temperature and mixed thoroughly prior to finishing to ensure consistency proper dispersion of the sanding agents.

SANDING: Substrate should be sanded with 180 grit sandpaper prior to staining or applying sealer. Stains should be allowed to dry prior to application of seal coat. Sand sealer with 320 grit or Superfine sponges. ELSEAL550 is designed to be used underneath ELAC550xx Envirocryl No-Sag Topcoat. Do **not** use as a sealer for EL100XX Line.

RECOMMENDED APPLICATION:	Spray type:	Air Assist Airless
	Fluid Pressure:	~800-1200 PSI
	Air Pressure:	25-35 PSI (depends on tip used)
	Tips:	04 or 06
	Wet Film Build:	6-8 mils
	Number of Coats:	1
	Drying Times:	See Below
	Maximum Dry Film Build:	6-8 mils (total system)

*Not recommended to be applied by Cup Gun

PHYSICAL PROPERTIES:	Specific Gravity:	1.04 ± 2%
	Viscosity:	6400 cps @25°C
	Solids Content:	28% by weight
	Pot Life:	None
	Flash Point:	>75°C
	VOC's:	89 g/L, 0.74 lb/gal
	VOC's (Less Exempt):	251 g/L, 2.09 lb/gal

EnviroLak

Technical Data Sheet
ELSEAL550
Revision Date: 11/8/2019

DRYING TIMES: Dry time for this product line varies depending on wet mils applied.

Air dry: (20°C/68°F)	Dry to Touch	5-20 Minutes
	Dry to Sand	1-2 Hours
	Dry to Stack	8-16 hours

Note: Gentle air movement (recirculator or fan) while parts are drying will reduce dry to sand times by 20-40%

Conventional Oven: (40-45°C/104-113°F)	Dry to Touch	5-10 Minutes
	Dry to Sand	15-50 Minutes
	Dry to Stack	3-6 Hours

Sun-Spot IR Cure: (Recommended)	Flash off	5 Minutes
	Cure	10 Minutes @60-70°C
	Cool Down	5-10 Minutes
	Product is dry to sand (or stack) after cooling	

GENERAL INFORMATION: Use stainless steel (304/316) equipment for all water based products. When switching between solvent and water based products in the same spray equipment we suggest the following:

From Solvent to Water: Wash with acetone, then wash with water.

From Water to Solvent: Wash with water, then wash with acetone.

Keep containers closed when not in use and wash all equipment well. Keep from freezing.

These products are designed for industrial use only. Please refer to the Safety Data Sheet prior to use.

SHELF LIFE: 12 months in unopened containers

STORAGE: Store in a tightly closed container at room temperature (18-25°C/64-75°F) and protect from direct sunlight and foreign material. Do not store at temperatures below 5°C/41°F.

Disclaimer: Every reasonable precaution is taken by the manufacturer in the manufacture of our products to ensure that they comply with our standards. The information given herein is correct to the best of our knowledge. Any suggestions made by us covering the use of our products are based on experience and/or tests believed to be reliable. However, because the use of any product of our manufacture is completely beyond our control, including for example, the method and conditions of application, no guarantee or warranty, expressed or implied, is made. Manufacturer's maximum liability shall be to replace such quantity of product determined by our laboratory to be defective. User shall determine the suitability of the product for his intended use and assumes all risk and liability in connection therewith.

Manufactured in Canada by Performance Finishing Solutions
4800 Eastgate Parkway, Units 3&4, Mississauga, Ontario, L4W 3W6
Tel: (905) 629-7007 Fax: (905) 629-7865
www.envirolak.com

 **Performance**
Finishing Solutions